

CEMSEAL LEAKPROOF

Fiber Reinforced Elastomeric Acrylic Waterproofing Membrane

DESCRIPTION

CEMSEAL LEAKPROOF is a fiber reinforced elastomeric acrylic waterproofing membrane. It is formulated with selected elastomeric and resilient acrylic polymers and reinforcing polyester fibers. Upon curing, it forms a thick, seamless, durable membrane thus offering ultimate waterproofing. It conforms to ASTM D 412-02, BS EN 12390, ASTM D 4587, ASTM D 4541 & ASTM C 1202-97.

ADVANTAGES

Waterproofing Waterproofing protection of up to 7 bars hydrostatic pressure.	High sheen High sheen, brilliant white colour and thick coat results in high levels of heat reflectance.
Crack bridging Unmatched crack bridging ability due to elastomeric properties.	Anti carbonation Reduces carbon dioxide and chloride ion diffusion thus protecting re-bars against corrosion.
Mechanical strength Reinforced for superior abrasion resistance.	Use & maintenance Single pack, easy to apply and simple re-coating
Adhesion Strong adhesion to masonry substrates.	Algae / Alkali / Fungus / UV Resistant Reduction in 6 - 7°C temperature.

SPECIFICATION SPECIFICATION

Available Packs	: 1,4,10,20 Litres
Colour	: White
Recommended System	: On RCC, plaster or primer, using brush or roller
Coverage	: 10 sq. ft/ltr for double coat on terraces 30-35 sq. ft/ltr for double coat on vertical walls
Drying time	: 4 - 6 hours @25°C (in dry weather)
Recommended Usage	: Can be used on roofs, terraces, parapet, sunshades and vertical walls. It can also be applied on existing IPS, sound brick-bat coba or cementitious waterproofing.
Shelf Life	: 2 years from date of manufacturing in original tightly closed containers away from direct sunlight and excessive heat

TECHNICAL DETAILS

a. Form	: Ready to use viscous liquid
b. Mix Density	: 1.26 + 0.02
c. Application temperature	: 5°C to 50°C



PRE PAINTING STEPS

PLASTER	: New masonry surfaces must be allowed to cure completely. It is recommended to allow 28 days as the curing time for new masonry surfaces.
CLEANING	: Surface should be free from any loose paint, dust or grease. Remove all existing bitumen coatings completely. It is recommended to use intense wire brushing or high speed water jet for thorough cleaning.
REPAIRING	: The substrate must be checked for its soundness using small hammer. All cracks at corner joints, channels and parapets should be properly treated.
FILLING FOR CRACKS	: For filling cracks upto 3mm use CEMSEAL KRACKFILL & CEMSEAL KRACKFILL+. Bigger cracks, damaged portions and hollow areas must be repaired with polymer modified cement mortars.

APPLICATION PROCESS

- Application should be done as per the company's recommended system.
- Coverage should be 15 sq.ft/kg for 3 coats. (1 coat diluted + 2 undiluted coat)
- All cracks should be filled with Mixture of CEMSEAL KRACKFILL and CEMSEAL KRACKFILL before applying LEAKPROOF.
- Corner tape and roof tape should be applied between 2 undiluted coats of LEAK PROOF.
- If your terrace is covered with Tiles or China Mojek then need to apply CEMSEAL CEMCRETE as primer coat before application of LEAKPROOF
- Terrace parapet walls need to be covered while applying LEAKPROOF.

POST PAINTING CARE

For the best performance of the LEAKPROOF, ensure proper washing and cleaning of all algae and fungal growth, if any, at regular intervals of six months.

PRECAUTIONS

- Do not apply during rains or extreme temperatures.
- Avoid abuses which may lead to puncturing of membrane.
- Ensure that the product is applied at least 6 inches inside the drain pipe.
- For best results, apply parapet to parapet to envelope the entire building.

WARRANTY

10 years Waterproofing warranty on terraces and vertical surfaces (please refer to warranty booklet for details).

SAFETY FEATURES

- Store the container with the lid tightly closed in an upright position, in a cool, dry place
- Keep out of reach of children and away from eatables.
- May be harmful if swallowed. In case of ingestion seek immediate medical attention.
- Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- In case of skin contact immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.
- Do not breathe vapour or spray. It is recommended to wear suitable nose pad during sanding and surface preparation to avoid dust inhalation
- Do not pour leftover paint down the drain or in water courses.
- In the event of spills, contain spillage using sand or earth.
- No added Lead, Mercury or Chromium compounds.

TECHNICAL INFORMATION & SERVICES

Further information and advice including practical demonstration are freely available from the technical service department of Cemseal Industries Ltd.

NOTE

- Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local Cemseal representative.
- Cemseal reserves the right to have the true cause of any difficulty determined by accepted test methods.

Address

Plant 1 :C-1/B-96-97 G.I.D.C Industrial Estate, Kalol, Panchamahar, Gujarat - 389330

Plant 2 :Plot no 30, Marble Market Sejbahar, Rajpur, Chhattisgarh - 492015

Web : www.cemseal.net | **Contact no** : +91 90992 66166